



# PICOFILM SR-270 K1

matt 7827, 305 g/m<sup>2</sup>

Top coated thermal film with standard sensitivity and very good resistance against external influences

## General tips

For quality reasons PICOFILM should be stored originally packed.

Storage and converting conditions of 23±5°C and 50±10% relative humidity are recommended. Exposure to strong artificial light or direct sunlight and any contact with aggressive chemicals should be avoided.

## Physical data

Name	Value	Tolerance	Norm
Thickness (total) [µm]	250	±12	ISO 534
Weight [g/m <sup>2</sup> ]	305	±12	ISO 536
Smoothness (Bekk) [s]	> 400		ISO 5627
ISO Brightness [%]	> 85		ISO 2470-1
Tear strength MD [MPa]	> 80		ISO 527-3/2/300
Tear strength CD [MPa]	> 80		ISO 527-3/2/300
Opacity [%]	> 97		ISO 2471

## Durability

Minimum 12 years under adequate storage conditions.

## Technologies

