

PRESSURETAC TOP 120 STRONG

matt 7748, 137 g/m²

Linerless, self-adhesive paper for automatic labelling in beverage logistics. Its additional weight and stiffness make PRESSURETAC Top 120 Strong ideal for use with label applicators, as well as wrap-around loop tags applied by hand.

PRESSURETAC Top 120 Strong is a satin-finished, FSC® certified 140g topcoat thermal paper with a reverse coating that only sticks to itself. There is no need for waste-intensive silicone paper, making PRESSURETAC an environmentally friendly alternative to conventional self-adhesive topcoat thermal paper.

PRESSURETAC Top 120 Strong is supplied in roll format and can be used immediately. No punching or perforation is required when the thermal printer has a cutter or perforation blade fitted. Text or variable information is direct thermal printed. The paper is optimised for Flexo pre-printing; it's possible to partially print the adhesive layer too.

Advantages

- Only sticks together coating to coating
- Reduced risk of accidents during processing as no silicone paper to discard
- Can be removed without any hint of residue – no cleaning required on wire mesh crates, cages, trays, trolleys or tensioning straps
- Ready-to-use for the final application – no punching / perforation required
- Variable material thickness – appropriate for manual and mechanical application
- Environmentally friendly as FSC® certified and without silicone paper (linerless)
- Suitable for use in all storage rooms - at temperatures of -20°C to +30°C
- Bisphenol-free



Technologies



Properties



- Sticks to itself
- Residue-free removal

General tips

For quality reasons PRESSURETAC should be stored originally packed. Storage & converting conditions of 23±5°C and 50±10% rel. humidity are recommended.

Physical data

Name	Value	Tolerance	Norm
Weight [g/m ²]	137	±10	ISO 536
Thickness (total) [µm]	141	±12	ISO 534
Smoothness (Bekk) [s]	> 250		ISO 5627
ISO Brightness [%]	> 85		ISO 2470-1
Bending stiffness MD [mN]	> 130		ISO 2493-1; 15°/10mm
Bending stiffness CD [mN]	> 90		ISO 2493-1; 15°/10mm
Tensile strength MD [N/15mm]	> 80		ISO 1924-3/2/300
Tensile strength CD [N/15mm]	> 40		ISO 1924-3/2/300
Opacity [%]	> 95		ISO 2471
Application temperature [°C]	-5 bis +30		

Durability

The product can be stored original packed for at least 12 months under these conditions.

Printing instructions

Printing and processing recommendations are available for download.